

Technical Data Sheet

| DESCRIPTION | | | |
|------------------------------|---------------------|-------------------|-------------------------------|
| Type of flooring | ISO10581(EN649) | | Homogeneous flooring |
| Total thickness | ISO24346(EN428) | mm | 2 |
| Weight | ISO23997(EN430) | g/sqm | 3250 |
| Width of sheet | ISO24341(EN426) | m | 2 |
| Length of sheet | ISO24341(EN426) | m | 20 |
| PERFORMANCES | | | |
| Abrasion resistance | EN660-2 | mm ³ | <=2.0 |
| Abrasion group | EN649 | group | P |
| Residual indentation | ISO 24343 -1(EN433) | mm | <=0.03 |
| Dimensional stability | EN434 | % | <=0.4 |
| Castor chair test | EN425 | | Good |
| Colour fastness | ISO105-B02 | degree | >=6 |
| Chemical products resistance | ISO26987(EN423) | | Good |
| Anti-bacterial | ISO846-C | | no support growth of bacteria |
| TVOC after 28 days | ISO16000-9 | ug/m ³ | <=10 |
| Flexibility | ISO24344(EN435) | mm | <=20 |
| Fire rating | GB 8624-2012 | Class | B1 |
| | EN11001-1 | Class | Bf1 S1 |
| Dop test | EN 14372:2004 | | No support growth of bacteria |
| Slip resistance | DIN51130 | Class | R9 |

Website address : www.WanabiWood.co.ZA

Contact: 27 (11) 028-9498

Email address : orders@wanabiwood.co.ZA

